

## SD MARINE BTB

## 醇酸面漆

### PRODUCT DESCRIPTION

#### 产品简介

A finish based alkyd resin and pigments.  
由醇酸树脂和着色颜料组成的醇酸面漆。

### RECOMMENDED USE

#### 用途

For steel structure in non immersion areas.  
用于非浸没区域的钢结构表面。

### FEATURES

#### 产品特性

Quick drying  
干燥迅速  
High gloss and good weathering resistance  
良好的光泽和耐候性  
Good abrasion resistance  
良好的耐磨性  
Good workability  
良好的施工性能

### PHYSICAL PROPERTIES

#### 基本数据

#### Color

#### 颜色

Colors  
各色

#### Finish

#### 光泽

Gloss  
有光

#### Volume Solids

#### 体积固体份

55%

#### Flash Point

#### 闪点

Greater than 29°C  
29°C 以上

#### Film thickness

#### 涂装膜厚

Dry : 25-40 microns/coat      Wet : 45-73microns/coat  
干膜: 25-40 微米/道      湿膜: 45-73 微米/道

#### Theoretical Coverage

#### 理论涂布率

0.083kg/m<sup>2</sup>/40microns  
0.083 千克/平方米/40 微米  
Practical coverage depending on surface conditions, environment, applications, etc.  
实际涂布率与表面处理, 外界环境, 施工方法等多种因素有关。

### APPLICATION

#### 施工

#### Application Temperature

#### 施工温度

-5°C-40°C

#### Mixing

#### 混合

Mix thoroughly with power agitator  
使用动力工具搅拌均匀

#### Mixing Ratio

#### 混合比例

One component coating  
单组份涂料

#### Application Methods

#### 施工方法

Airless spray, air spray, brush and roller  
无气喷涂、空气喷涂、刷涂、滚涂

## Airless spray 无气喷涂

Nozzle tip	喷嘴尺寸	0.43mm-0.53mm
Nozzle pressure	出口压力	≥10Mpa
Thinning ratio	稀释比率	0-10% by weight (重量比)

## Brush/Roller 刷涂、滚涂

Thinning ratio	稀释比率	0-10% by weight (重量比)
----------------	------	-----------------------

## Thinner

稀释剂

## SD MARINE Paint Thinner

专用稀释剂

## Drying time &

## Overcoating interval

干燥时间&涂装间隔

Temperature	温度	-5℃	5℃	20℃	30℃
Surface dry	指触干燥	4hrs	2hrs	1hr	1hr
Touch dry	半硬干燥	30hrs	20hrs	7hrs	5hrs
Min. interval	最小涂装间隔	36hrs	24hrs	10hrs	8hrs
Max. interval	最大涂装间隔				

## Typical undercoat

适用下涂

## SD MARINE PRIMER

醇酸底漆

## Typical topcoat

适用上涂

## STORAGE

贮存

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed.

贮存于干燥阴凉的环境中，远离热源及火源。包装桶必须保持封闭。

## Shelf life

贮存期限

12months from date of production (25℃)

自生产之日起 12 个月 (25℃)

## DISCLAIMER

提请注意

The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development. Please check this data sheet is current prior to using the product.

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制, 此中信息不含担保, 即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展, 本说明书的内容也会随时进行更改, 此中所有信息均以我方确认为主。产品使用前, 请确认所持说明书为最新版本。

[www.kansai.com.cn](http://www.kansai.com.cn)

Issued Date 2011/6/27

发行日期 2011/6/27