

Protective Coatings

RUSTITE NC 90 特种快干底漆

PRODUCT DESCRIPTION A rust preventive primer based on modified alkyd resin and anti-rust pigments.

产品简介 由改性醇酸树脂和防锈颜料组成的防锈底漆

RECOMMENDED USE For steel structure in non immersion areas and compatible with many kinds of topcoats,

用途 including epoxy paint and polyurethane paint.

用于非浸没区域的钢结构表面。可以与多种面漆配套,包括环氧面漆和聚氨酯面漆。

FEATURES Good corrosion resistance

产品特性 良好的防腐性能

Compatibility with many finish systems

可以同多种面漆配套 Good workability 良好的施工性能 Quick drying 干燥迅速

PHYSICAL PROPERTIES

基本数据

ColorOxide Red, Grey颜色铁红色, 灰色

Volume Solids 47%

体积固体份

VOC464g/L, accord with EU Directive2004/42/EC, subcategory j挥发性有机化合物含量464 克/升,符合欧盟溶剂排放指令 2004/42/EC, j 子类别

Flash Point Greater than 40° C

闪点 40℃以上

 Film thickness
 Dry: 25-50 microns/coat
 Wet: 53-106microns/coat

 涂装膜厚
 干膜: 25-50 微米/道
 湿膜:53-106 微米/道

 Theoretical Coverage
 0.128kg/m²/40microns

 理论涂布率
 0.128 千克/平方米/40 微米

Practical coverage depending on surface conditions, environment, applications, etc.

实际涂布率与表面处理, 外界环境, 施工方法等多种因素有关。

APPLICATION

施工

Application Temperature $-5^{\circ}\text{C}-40^{\circ}\text{C}$

施工温度

Mix thoroughly with power agitator

混合 使用动力工具搅拌均匀 **Mixing Ratio** One component coating

混合比例 单组份涂料

Application MethodsAirless spray, air spray, brush and roller施工方法无气喷涂、空气喷涂、刷涂、滚涂





Airless spray 无气喷涂

喷嘴尺寸 0.33mm-0.43mm Nozzle tip

Nozzle pressure 出口压力 ≥10Mpa

Thinning ratio 稀释比率 0-10% by weight (重量比)

Brush/Roller 刷涂、滚涂

Thinning ratio 稀释比率 0-10% by weight (重量比)

Thinner Paint Thinner X 稀释剂 稀释剂X

5℃ 20℃ 30℃ Drying time & Temperature 温度 Overcoating interval Surface dry 指触干燥 30mins 20mins 1.5hrs 干燥时间&涂装间隔 半硬干燥 1hr 30mins Touch dry 2.5hrs

Min. interval

Max. interval 最大涂装间隔

最小涂装间隔

4hrs

2hrs

2hrs

Applied substrate Bare steel 适用底材 裸钢

Typical topcoat SD MARINE BTD or according to the coating system of Cosco Kansai.

适用上涂 醇酸面漆或参考我司涂装配套

STORAGE Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept

tightly closed.

贮存于干燥阴凉的环境中,远离热源及火源。包装桶必须保持封闭。

Shelf life

12months from date of production (25°C)

贮存期限 自生产之日起 12 个月(25℃)

DISCLAIMER The information given on this sheet is to the best of our knowledge and accurate at the time of 提请注意 issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product

development. Please check this date sheet is current prior to using the product.

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所 能控制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺 的不断发展,本说明书的内容也会随时进行更改,此中所有信息均以我方确认为主。产品

使用前,请确认所持说明书为最新版本。

www.kansai.com.cn

贮存

Issued Date 2011/6/27 发行日期 2011/6/27